

Noxudol 900 D

Underbody coating

General

Noxudol 900 D is a thixotropic, chemically stabilized product consisting of bitumen, waxes, rust inhibitors and solvents. The product is used on the underside of the vehicle and offers preventive rust protection and reliable abrasion protection.

Range of application

Noxudol 900 D is especially composed for car under body and can be applied by conventional high-pressure pumps in different thicknesses.

The product gives a good anticorrosive protection, de-icing salt protection and some abrasion protection depending on thickness applied.

Noxudol 900 D is also suitable for long time outdoor storing of industrial products, for example untreated steel surfaces, machines etc.

Instructions for use

Make sure that the surface is dry and free from oil, dirt and rust. Equipment for airless high pressure spraying 1:26 is recommended for treatment of car under bodies and fenders. The product can also be brushed on.

Areas with rust should be treated with **Noxudol 750 / Mercasol 831 ML** before in order to achieve best result possible. Apply several layers of Noxudol 900 D where increased protection is required. The car is ready for usage immediately after application.

Package

30011521 / 1-lit can (12 pcs per pack.)
30010408 / 20-lit can

Technical data

Color:	Black
Consistency:	Thixotropic
Type of film:	Elastic, dry film
Density at 20° C:	1040 ± 20 kg/m ³
Dry content:	65 ± 3 %
Solvent:	White spirit
Film thickness:	150 – 500 µm
Application temperature:	15 - 25° C
Removal with:	White spirit or degreasing compound
Storing time:	12 months
Storing temperature:	5 - 35° C

For further information we recommend the safety data sheet or instruction on package

Issue: 2015-01-14

