

Noxudol UM-1600

Highly thixotropic underbody coating

General

Noxudol UM-1600 is a highly thixotropic, fiber reinforced product, based on bitumen, waxes and low aromatic solvent.

Range of application

Noxudol UM-1600 is a durable anticorrosive to be used under the fender, wheelhouse and on the remainder of the underbody, where extra effective protection is required. When applied in thicker layers it also provides a good sound damping effect.

Instructions for use

Make sure that the surface is dry and free from oil, dirt and rust. Apply Noxudol UM-1600 on a dry surface with low pressure (airmix) 1:3 equipment, spray gun or brush to the vehicle underbody and wheelhouse. We recommend to prime rusty surfaces with Noxudol 750 / Mercasol 831 ML. Apply several layers with Noxudol UM-1600 when a powerful rust protection is needed.

Package

31501511 / 1-lit plåtflaska (12 st per förp.)
31500408 / 20-lit burk

Technical data

Color:	Black
Consistency:	High thixotropic
Type of film:	Elastic
Density at 20° C:	1000 ± 40 kg/m ³
Dry content:	70 ± 5 %
Solvents:	White spirit
Film thickness:	0,5 – 1,5 mm
Application temperature:	15 - 25° C
Removal with:	Wash with a degreaser based on white spirit, detergent or alkali
Storing time:	12 months
Storing temperature:	5 - 35 ° C

For further information we recommend the safety data sheet or instruction on package

Issue: 2015-01-14



Auson AB, Kungsbacka, Sweden
T: +46 (0)300-56 20 00
www.auson.se

Dessa anvisningar och information är avsedda att vägleda förbrukaren vid användning av produkten och lämnas utan förbindelse. Vid oklarhet tillråds egna prov eller skriftliga råd från oss.

Noxudol